



DOMINICO TEX

A. Material Descriptions

Fabric Name; DOKDO-SKYDIVING-SS	Finishing Type; SILICONE/SILICONE COATING
Fabric Width; Min.155CM	Fabric Pattern; Ripstop
Yarn Material; PA 6.6(30DENIER) 100%	Use : Top & Bottom for SKYDIVING

B. Technical Specifications

Test Conducted	Test Method	Test Part	Test Unit	Lower Limit	Upper Limit	Test Result
Tensile Strength (Breaking Strength)	ISO 1421:1998	Warp	daN/5cm	35	40	40
		Weft	daN/5cm	35	42	42
Elongation	INTERNAL METHOD	3 lbf/BIAS	%	5	15	13.3
	DOMINICO	5 lbf/BIAS	%	10	20	17.2
		10 lbf/BIAS	%	20	30	22.8
Air Permeability	ISO 9237:1995	100cm ² /2000Pa	l/m ² /min	6	20	6
Air Permeability	EM ISO 9237	125Pa,20cm ²	ft ³ /ft ² /min	0	0	0
Tearing Strength	ISO 4674-2:1998	Warp	daN	3	5.8	5.8
		Weft	daN	3	4.5	4.5
Weight	ISO 2286-2:1998		g/m ²	41	45	43
Thread Count	ASTM D 3775-1998	Warp	thread/inch	137	142	139
		Weft	thread/inch	134	139	136